Rayan Polymer Industry



Masterbatches, Compounds and Polymer Additives Supplier

Technical Data Sheet

Product Name: Mineral Filled Polypropylene Compound

Grade: RP71PHS-50TD-B

Description:

RP71PHS-50TD-B is virgin polypropylene filled with talc powder. It provides good stiffness and dimensional stability. This compound has been specifically designed for extrusion process for producing profiles and sheets.

General Information:

Material Status: Commercially Active

Delivery form: Pellets
Color: Black

Processing Method: Profile extrusion, Injection Molding

Application: Profile parts

Packing: 25 kg

Characteristics:

	Value	Unit	Test method
Density	1.45	gr/cm ³	ASTM D 792
MFI (230 °C, 2.16 Kg)	3	gr/10min	ASTM D 1238
Tensile Strength (50 mm/min)	22	MPa	ASTM D 638
Flexural Modulus	3400	MPa	ASTM D 790
Izod Notched Impact Strength	NA	J/m	ASTM D 256

Recommendation:

- The recommended processing temperature is 170 to 240 °C
- Store in dry place away from direct sun exposure

Published Aug, 2023

Web-site:www.rayanbaspar.comTel: +98 21 4478 7085E-mail:rayanbaspar.ind@gmail.comFax: +98 21 4478 7085

Address: Polymer Technology Incubator (IPPI), Km 15, Tehran-Karaj high way, Tehran, Iran