Rayan Polymer Industry



Masterbatches, Compounds and Polymer Additives Supplier

Technical Data Sheet

Product Name: Mineral Filled Polypropylene Compound

Grade: RP71PRMI-20TD-B

Description:

RP71PRMI-20TD-B is recycled polypropylene filled with talc. It provides good impact strength and dimensional stability. This compound has been specifically designed for automotive plastics parts. Its main application is injection molding process.

General Information:

Material Status: Commercially Active

Delivery form: Pellets **Color:** Black

Processing Method: Injection Molding **Application:** Automotive parts

Packing: 25 kg

Characteristics:

	Value	Unit	Test method
Density	1.05	gr/cm ³	ASTM D 792
MFI (230 °C, 2.16 Kg)	8	gr/10min	ASTM D 1238
Tensile Strength (50 mm/min)	20	MPa	ASTM D 638
Flexural Modulus	1700	MPa	ASTM D 790
Izod Notched Impact Strength	7	KJ/m^2	ASTM D 256

Recommendation:

- The recommended processing temperature is 160 to 230 °C
- Store in dry place away from direct sun exposure

Published July, 2021

Web-site:www.rayanbaspar.comTel: +98 21 4478 7085E-mail:rayanbaspar.ind@gmail.comFax: +98 21 4478 7085

Address: Polymer Technology Incubator (IPPI), Km 15, Tehran-Karaj high way, Tehran, Iran