

Technical Data Sheet

Product Name: **Mineral Filled Polypropylene Compound**

Grade: **RP72PMI-20CC-N**

Description:

RP72PMI-20CC-N is polypropylene filled with fine and treated calcium carbonate. It provides good stiffness and impact resistance. This compound has been specifically designed for general injection molding parts.

General Information:

Material Status:	<i>Commercially Active</i>
Delivery form:	<i>Pellets</i>
Color:	<i>Natural</i>
Processing Method:	<i>Injection Molding</i>
Application:	<i>Home Appliance, Electrical Plastics Parts, Housewares, etc</i>
Packing:	<i>25 kg</i>

Characteristics:

	<i>Value</i>	<i>Unit</i>	<i>Test method</i>
Density	1.05	gr/cm ³	ASTM D 792
MFI (230 °C, 2.16 Kg)	7	gr/10min	ASTM D 1238
Tensile Strength (50 mm/min)	25	MPa	ASTM D 638
Flexural Modulus	1700	MPa	ASTM D 790
Izod Notched Impact Strength	85	J/m	ASTM D 256

Recommendation:

- *The recommended processing temperature is 170 to 230 °C*
- *Store in dry place away from direct sun exposure*

Published July, 2021

Web-site: www.rayanbaspar.com

E-mail: rayanbaspar.ind@gmail.com

Tel: +98 21 4478 7085

Fax: +98 21 4478 7085

Address: Polymer Technology Incubator (IPPI), Km 15, Tehran-Karaj high way, Tehran, Iran