

Technical Data Sheet

Product Name: ***Polypropylene Reinforced with Glass Fiber***

Grade: ***RP73PHS-30GF-N***

Description:

RP73PHS-30GF-N is virgin polypropylene reinforced with 30 % glass fiber. It combines excellent mechanical properties and toughness and also appropriate thermal resistance. This grade provides high tensile strength and stiffness. This compound has been designed for injection molding process and its main application is automotive parts and electrical goods.

General Information:

Material Status:	<i>Commercially Active</i>
Delivery form:	<i>Pellets</i>
Color:	<i>Natural</i>
Processing Method:	<i>Injection Molding</i>
Application:	<i>Automotive Plastics Parts</i>
Packing:	<i>25 kg</i>

Characteristics:

	<i>Value</i>	<i>Unit</i>	<i>Test method</i>
Density	1.15	gr/cm ³	ASTM D 792
Tensile Strength (50 mm/min)	85	MPa	ASTM D 638
Elongation	6-7	%	ASTM D 638
Flexural Modulus	5500	MPa	ASTM D 790
Izod Notched Impact (23°C)	10	KJ/m ²	ASTM D 256

Recommendation:

- *It should be degassed properly before using*
- *The recommended processing temperature is 180 to 240 °C*

Published September, 2021

Web-site: www.rayanbaspar.com

E-mail: rayanbaspar.ind@gmail.com

Tel: +98 21 4478 7085

Fax: +98 21 4478 7085

Address: Polymer Technology Incubator (IPPI), Km 15, Tehran-Karaj high way, Tehran, Iran